

MPCM 28D

Microencapsulated Phase Change Material
Phase Change: 28°C, 82.4°F



DESCRIPTION

Micro-encapsulated phase change materials (MPCMs) are an effective solution that combines reliable thermal control with excellent mechanical stability and easy dispersibility. These characteristics allow it to be used in a wide range of formulations and manage temperature peaks for a variety of applications.

APPLICATIONS

The applications for phase change materials are limited only by the imagination. Some common uses for MPCM at this temperature include:

- **Bedding** – to provide desired human comfort requirements such as a cool touch effect to mattresses, pillows, and mattress ticking.
- **Building Materials** – to increase the energy efficiency of residential and commercial buildings.
- **Consumer Textiles** – to provide desired human comfort requirements such as cool touch effect to fabrics or the ability to keep people cool when material is worn close to the body.

PACKAGING

Dry powder is generally shipped in 55-gallon fiber drums of 140 pounds net weight or in super sacks of 650 pounds.

PROPERTIES

MPCM 28D typically exhibits these general properties:

Typical Properties

Appearance	White to slightly off-white color
------------	-----------------------------------

Form	Dry powder ($\geq 97\%$ solids)
------	----------------------------------

Particle size (mean)	15-30 micron
----------------------	--------------

Melting point	28°C, 82.4°F ($\pm 2^\circ\text{C}$)
---------------	--

Heat of fusion	≥ 175 J/g
----------------	----------------

HEALTH AND SAFETY

Please refer to the Safety Data Sheet (SDS) for necessary safety and handling precautions for this product.

Visit www.microtek-labs.com or call 937.236.2213 for more information on your thermal management needs.

IMPORTANT NOTE: This data has been compiled from testing that Microtek Labs believes reliable and is supplied for informational purposes only. Microtek Labs encourages purchasers to validate this data and the product's fitness for use in the purchaser's process by performing their own tests.

MT20-011 MPCM 28D PDS © 2020 Microtek Laboratories, Inc. All Rights Reserved.
All other trademarks are the properties of their respective owners.

MPDS3300-0027

Revision 1

Effective Date: 05/07/2020

microtek
laboratories, inc.