# nextek 6D

**Microencapsulated Phase Change Material** Phase Change: 6°C, 42.8°F

# DESCRIPTION

**nextek** is the next level in PCM technology and performance. Nextek's patented capsule wall technology combines robustness, high thermal stability, and easy dispersability. It is versatile enough to be used in a variety of uses and formulations.

# **APPLICATIONS**

The applications for phase change materials are limited only by the imagination. Some common uses for nextek PCM at this temperature include:

• **Packaging and Shipping** – to protect temperature sensitive materials in storage and transit.

### PACKAGING

Dry powder is generally shipped in 55-gallon fiber drums of 140 pounds net weight or in super sacks of 650 pounds.

# HEALTH AND SAFETY

Please refer to the Safety Data Sheet (SDS) for necessary safety and handling precautions for this product.

# PROPERTIES

nextek 6D typically exhibits these general properties:

Typical Properties	
Appearance	White to slightly off-white color
Form	Dry powder (≥ 97% solids)
Particle size (mean)	15-30 micron
Melting point	6°C, 42.8°F (±2°C)
Heat of fusion	≥170 J/g

Visit **www.microteklabs.com** or call **937.236.2213** for more information on your thermal management needs.

IMPORTANT NOTE: This data has been compiled from testing that Microtek Labs believes reliable and is supplied for informational purposes only. Microtek Labs encourages purchasers to validate this data and the product's fitness for use in the purchaser's process by performing their own tests.

MT18\_002 Nextek 6D PDS © 2018 Microtek Laboratories, Inc. All Rights Reserved. All other trademarks are the properties of their respective owners.

MPDS3300-0048

Revision 2

Effective Date: 03/19/2020



