



# 24D

Microencapsulated  
Phase Change Material  
Phase Change: 24°C, 75.2°F

## DESCRIPTION

**Micronal** is an acrylic PCM. It is primarily used as a functional component in foams, building materials, and thermal management systems, for temperature regulation to improve comfort and climate conditions.

## APPLICATIONS

The applications for phase change materials are limited only by the imagination. Some common uses for Micronal at this temperature include:

- **Bedding** – to provide desired human comfort requirements such as a cool touch effect to mattresses, pillows, and mattress ticking.
- **Building Materials** – to increase the energy efficiency of residential and commercial buildings.

## PACKAGING

Dry powder is generally shipped in fiber drums (64 kg) or super sacks (295 kg).

## HEALTH AND SAFETY

Please refer to the Safety Data Sheet (SDS) for necessary safety and handling precautions for this product.



## PROPERTIES

**Micronal 24D** typically exhibits these general properties:

Typical Properties	
Appearance	White to slightly off-white color
Form	Dry powder (≥ 98% solids)
Particle size (mean)	ca 50 – 300 micron
Melting point	24°C, ± 2°C
Heat of fusion	105 J/g

Visit [www.microteklabs.com](http://www.microteklabs.com) or call 937.236.2213 for more information on your thermal management needs.

IMPORTANT NOTE: This data has been compiled from testing that Microtek Labs believes reliable and is supplied for informational purposes only. Microtek Labs encourages purchasers to validate this data and the product's fitness for use in the purchaser's process by performing their own tests.

MT23-011 Micronal 24D PDS © 2023 Microtek Laboratories, Inc. All Rights Reserved.  
All other trademarks are the properties of their respective owners.

MPDS3300-0061

Revision 4

Effective Date: 01/18/2024



a CAU group company